



**MANUFACTURER**  
**Iris U.S.**

1360 S Vernon Street, Anaheim, CA 92805

Telephone: 800.323.9906  
Fax: 866.398.4747  
Web: [www.irisus.com](http://www.irisus.com)

**1. PRODUCT NAME**

**Large Format Slabs**



**Zenit White**



**Maestro Carrara Zebrino**




**Maestro Bernini Classico**




**Maestro White Statuario**




**Maestro Bernini Oro**



**Maestro Taj Mahal**



**Maestro Platinum Grey**



**2. PRODUCT DESCRIPTION**



(Green Choice includes pre-consumer recycled materials and post-consumer recycled materials)

Iris US proudly contains factory and products certifications:



**Size/thickness:**

60" x 126" x 1/2" nominal (available in polished finish only; countertops unrectified or natural)

60" x 120" x 1/4" nominal

60" x 60" x 1/4" nominal

30" x 60" x 1/4" nominal

30" x 30" x 1/4" nominal

**Finishes:**

Honed and Polished

**Recommended Grout Joint:** 3/32" or greater

All sizes modular with 3/16" grout joint (≈5 mm)

Grout joints of 1/8" inch or less, especially with larger format tiles or running bond patterns, may requires floor flatness values in excess of the 1/4" in 10' (or 1/16" in 1.0') standard required by ANSI.

See ANSI A108.01 2.6.2.2

For patterns with running bond/brick joints patterns Iris US recommends a maximum of 33% offset.

See ANSI A108.02 section 4.3.8

### 3. TECHNICAL DATA

Physical – Visual Properties	ASTM TEST	Industry Standard	Iris US Results
Water absorption	C373	Impervious <0.5%	≤0.1%
Thickness Dimension	C499	Range ± 0.04 Inc. Max.	≤±0.04 Inc.
Facial Dimension	C499	± 0.25 %	≤ ± 0.25%
Wedging	C502	± 0.25 %	≤ ± 0.25%
Bond Strength	C482	≥ 150 psi	≥200psi
Breaking Strength	C648	≥175 lbf	≥300lbf
Hardness (Mohs)	Scratch Test (No regulated)	Range 0 - 10	≥ 7
Deep Abrasion Resistance	C1243	Impervious (Porcelain) Class P1: ≤ 175mm	≤ 175mm
Visible Abrasion Resistance for Glazed tiles	C1027	No Requirement, Range 0 - 5	Class 4
Frost Resistance	C1026	No sample must show alterations to surface	No evidence of Damage
Robinson Test	AC627	As reported	Extra heavy
Chemical Resistance	C650	No Requirement, Range E - A	Class A
Stain Resistance	C1378	No Requirement, Range E - A	Class A*
DCOF	BOT 3000	≥0.42*	≥0.42 - ≤0.60 *
Aesthetic Classification	Visual Evaluation Shade & texture	No Requirement, Range V0 -V4	V1-V3
LRV (Light Reflectance Value)	C609	No Requirement, Range 0-100	10 to 80 depending on style/color selection

\* All values given are for matte or honed material. No values are given for polished material. Iris U.S. does not recommend polished surfaces in area subject to exposure from grease, oil or water.

For level interior spaces to be walked upon when wet (see ANSI A137.1 section 6.2.2.1.10 – Section 9.6 for test procedure).

The above information might be a subject to change.

### 4. INSTALLATION

All installation work using Iris US tiles will conform to the standards set forth in the latest version of ANSI A108/118 and/or the TCNA Handbook for Ceramic Tile installations.

Installation or setting materials:

Movement joints shall be provided throughout the tile and work will conform to ANSI Specification A108.01-3.7; A108.02 – 4.4. and TCNA Details EJ171.

Setting materials used will conform to the ANSI 118.4 standard or greater and be recommended by the selected manufacturer for the installation & setting materials for ceramic or porcelain tile based on the application requirements.

### 5. WARRANTY

Iris US guarantees that its products will be free of manufacturing defects and they will meet or exceed the performance specifications set forth in ANSI 137.1.

### 6. MAINTENANCE

#### Care and Maintenance Recommendations Guide

Please refer to **Iris US Care and Maintenance Recommendations Guide** for all technical information as to the care of this collection.

### 7. TECHNICAL SERVICES

#### Technical Assistance

Guide Specifications, literature, MSDS, tile samples, details and installation procedures are all available for your use or libraries.

Please contact your nearest Iris US representative for catalogues, physical samples, or architectural binders.